

19



Europäisches Patentamt

European Patent Office

Office européen des brevets



11 Publication number:

0 394 547 B1

12

EUROPEAN PATENT SPECIFICATION

- 45 Date of publication of patent specification: 24.05.95 51 Int. Cl.⁸: **C08K 13/02, C08L 57/08,**
//(C08K13/02,5:00,3:34,3:22,
21 Application number: **89114275.4** 5:05,3:16)
22 Date of filing: **02.08.89**

54 **Stabilized chlorine-containing resin composition.**

- | | |
|--|---|
| 30 Priority: 27.04.89 JP 106068/89 | 73 Proprietor: AKISHIMA CHEMICAL INDUSTRIES CO. LTD.
7-14, Nihonbashi Honcho-1-chome
Chuo-ku
Tokyo (JP) |
| 43 Date of publication of application:
31.10.90 Bulletin 90/44 | 72 Inventor: Tadenuma, Masahiko
556, Amema
Akigawa-shi (JP)
Inventor: Miyagi, Tetsuhiro
2-3-702, Tsutsujigaoka-3-chome
Akishima-shi (JP)
Inventor: Miyazawa, Tadashi
9-8, Nishionuma-2-chome
Sagamihara-shi (JP) |
| 45 Publication of the grant of the patent:
24.05.95 Bulletin 95/21 | 74 Representative: WILHELMS, KILIAN & PARTNER Patentanwälte
Eduard-Schmid-Strasse 2
D-81541 München (DE) |
| 64 Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE | |
| 56 References cited:
US-A- 4 659 764 | |

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 394 547 B1

Description

This invention relates to a thermally stabilized chlorine-containing resin composition. More particularly, this invention relates to a chlorine-containing resin composition comprising a chlorine-containing resin and a stabilizer consisting essentially of an overbased alkaline earth metal salt, zeolite, calcium hydroxide and a complex of a metal perchlorate with a polyhydric alcohol or its derivative, said composition having excellent resistance to the discoloration and deterioration in physical properties of the chlorine-containing resin, both accompanying the thermal degradation of the resin caused when the resin is subjected to thermoforming or exposed to a high temperature atmosphere for a long period of time.

When chlorine-containing resin compositions are subjected to thermoforming or when the molded articles of said compositions are exposed to high temperatures for a long period of time, they give rise to thermal degradation accompanied by dehydrochlorination, whereby discoloration and/or deterioration in physical properties of the resin are caused. In the case of the molded articles, the commercial value is reduced significantly. Hence, it has been conventional to add to chlorine-containing resins a stabilizer which is a combination of a salt of a carboxylic acid with a metal such as barium, zinc or the like with an organic ester of phosphorous acid, a phenolic antioxidant or the like to stabilize the chlorine-containing resins.

Molded articles obtained from such stabilized chlorine-containing resin compositions have recently been used in large quantities as interior parts of automobiles. In the case of a molded article of a chlorine-containing resin composition with a soft resin formulation, a urethane is injected into the interior of the molded article or laminated onto the back side of the molded article and foamed for the purpose of making automobiles lighter, improving the impact resilience and hand of the molded article and enhancing the safety of drivers. The molded articles thus obtained are utilized as interior parts of automobiles. Such interior parts of automobiles have been produced by subjecting a resin composition to calendaring or extrusion to obtain a sheet and then subjecting the sheet to vacuum forming. Therefore, the thermoforming conditions in this production are substantially the same as those in the production of general molded articles, and accordingly, the chlorine-containing resin compositions containing the above-mentioned known combination of stabilizing components are thermally stable enough under the thermoforming conditions. However, it has been difficult to form a complicated grain leather pattern on the surface of the above molded articles and even if the pattern can be formed the hand of the molded articles obtained is not satisfactory. Therefore, it has been designed to form a complicated grain leather pattern having an improved hand.

Under such circumstances, powder molding methods have been employed in recent years to realize said improvement. The powder molding methods are disclosed in, for example, JP-A-60-161451, JP-A-61-91238 and US-A-4,659,764.

In these prior art references, a molding method is adopted which comprises adding, to a chlorine-containing resin, a stabilizer, a plasticizer, a pigment, etc., mixing them thoroughly with heating (so-called dry-blending) to obtain a resin composition in the powder form, sprinkling the powder form resin composition on a metal mold at a high temperature of 200-280 °C by rotational powder molding or powder slush molding to fuse the powder particles, and cooling the fused product to obtain a molded article. The molded article for use as an interior part of automobiles obtained by the above powder molding has the advantage that the outermost layer thereof has a precise, complex, calm, leather-like pattern and hand. However, there are such problems that since, in the powder molding, a chlorine-containing resin composition in the powder form is sprinkled on a metal mold at a high temperature to fuse the powder particles without being beforehand subjected to kneading and gelation, a resin composition consisting of a chlorine-containing resin and a conventional amount of a conventional stabilizer tends to be thermally degraded with discoloration when it is subjected to the powder molding. Furthermore, there is a further problem that when the metal mold is repeatedly used in the powder molding of the above resin composition the molding surface of the metal mold is stained. In addition, the interior parts obtained by subjecting the molded article to integral molding with a urethane as a secondary processing are discolored when they are exposed to a high temperature of 80 - 130 °C for 300 hours or more, resulting in deterioration of quality.

In order to overcome the above severe thermal conditions in the powder molding, thermal stabilization of chlorine-containing resin with various stabilizers has so far been proposed. However, no sufficient stabilization is obtained and an improvement thereof has been desired.

This invention aims at providing a chlorine-containing resin composition which has been thermally stabilized with a stabilizer and which has solved the technical problems of (1) thermal stabilization of a chlorine-containing resin composition in thermoforming, particularly powder molding under the severe thermal conditions, (2) staining of metal mold in repeated powder molding and (3) discoloration of an integrally molded article of said resin composition with a urethane when the article has been subjected to a

high temperature for a long period of time.

According to this invention, there is provided a thermally stabilized chlorine-containing resin composition comprising a chlorine-containing resin and a stabilizer consisting essentially of (a) an overbased alkaline earth metal carboxylate or phenolate complex, (b) zeolite, (c) calcium hydroxide and (d) a complex of at least one metal perchlorate selected from the group consisting of sodium, magnesium, calcium and barium perchlorates with at least one compound selected from the group consisting of polyhydric alcohols and their derivatives.

The complex which is the component (a) of the stabilizer which is one of the constituents of the composition of this invention can be easily produced by reacting an excess equivalent of an alkaline earth metal oxide or hydroxide with an organic carboxylic acid, for example, a fatty acid of 7-18 carbon atoms, or with a phenol, for example, an alkyl phenol (the alkyl group thereof is at least one alkyl selected from the group consisting of octyl, nonyl and dodecyl), in a hydrocarbon solvent or a hydrocarbon-alcohol mixed solvent. This production process is disclosed in US-A-2,968,642; 2,971,014; 3,147,232; 3,533,975; 4,159,973; 4,252,698; etc. The complex includes, for example, overbased barium 2-ethylhexanoate, overbased barium isodecanoate, overbased barium oleate, overbased barium linoleate, overbased calcium isodecanoate, overbased calcium oleate, overbased magnesium oleate, overbased barium dodecylphenolate carbonate, overbased barium octylphenolate carbonate, overbased calcium dodecylphenolate carbonate, overbased calcium nonylphenolate carbonate, overbased calcium thiobisdodecylphenolate carbonate and overbased magnesium nonylphenolate carbonate. These overbased alkaline earth metal carboxylate and phenolate complexes can be produced easily; however, commercially available complexes may also be used. The commercially available complexes include, for example, Lubrizol LD 2105, LD 2106 and LZ 2116 which are all products of Lubrizol Corp. in U.S.A.

In this invention, the overbased alkaline earth metal carboxylate or phenolate complex is used in an amount of preferably 0.1 - 4 parts by weight, more preferably 0.2 - 2 parts by weight, per 100 parts by weight of the chlorine-containing resin.

The zeolite which is the stabilizer component (b) of this invention is a synthetic A type zeolite represented by the general formula, $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot y\text{H}_2\text{O}$ ($0.5 \leq x \leq 3$ and $0.5 \leq y \leq 6$). It includes, for example, $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot \text{SiO}_2 \cdot 4.5\text{H}_2\text{O}$ which is isometric ($a = 12.32 \text{ \AA}$). In this invention, it is advantageous that the zeolite has a particle diameter as small as possible. The weight average particle diameter of the zeolite is preferably 10μ or less. More preferably, the proportion of particles having particle diameters of $1-5 \mu$ is 90% or more. In this invention, the zeolite is used in an amount of preferably 0.1-5 parts by weight, more preferably 0.5-2 parts by weight, per 100 parts by weight of the chlorine-containing resin.

The calcium hydroxide which is the stabilizer component (c) of this invention is preferably in the particle form whose weight average particle diameter is 10μ or less. In this invention, the calcium hydroxide is used in an amount of preferably 0.5-8 parts by weight, more preferably 1-5 parts by weight, per 100 parts by weight of the chlorine-containing resin.

The complex of at least one metal perchlorate with at least one compound selected from polyhydric alcohols and their derivatives, which is the stabilizer component (d) of this invention, is preferably a complex represented by the general formula, $[\text{Me}(\text{ClO}_4)_n][\text{R}(\text{OH})_p]_q$ (Me is sodium, magnesium, calcium or barium; n is an integer of 1-2; p is an integer of 1-3; q is an arbitrary number of 1-6; R is the residue of a polyhydric alcohol or its derivative; and qR's may be the same or different), the complex being a liquid at ordinary temperature.

$\text{Me}(\text{ClO}_4)_n$ which is one of the constituents of the complex is sodium perchlorate, magnesium perchlorate, calcium perchlorate or barium perchlorate. In $[\text{R}(\text{OH})_p]_q$, R is the residue of a polyhydric alcohol or its derivative. The polyhydric alcohol and its derivative include, for example, ethylene glycol; ethylene glycol mono-C₁₋₄alkyl ethers such as ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol monoisopropyl ether, ethylene glycol monobutyl ether and the like; ethylene glycol monophenyl ether; ethylene glycol monobenzyl ether; diethylene glycol; diethylene glycol mono-C₁₋₄alkyl ethers such as diethylene glycol monomethyl ether, diethylene glycol monoethyl ether, diethylene glycol monobutyl ether and the like; triethylene glycol; triethylene glycol mono-C₁₋₄alkyl ethers such as triethylene glycol monomethyl ether, triethylene glycol monoethyl ether, triethylene glycol monobutyl ether and the like; polyethylene glycol; propylene glycol; propylene glycol mono-C₁₋₄alkyl ethers such as propylene glycol monomethyl ether, propylene glycol monoethyl ether, propylene glycol monobutyl ether and the like; dipropylene glycol; dipropylene glycol mono-C₁₋₄alkyl ethers such as dipropylene glycol monomethyl ether, dipropylene glycol monoethyl ether and the like; tripropylene glycol; 1,4-butanediol; 1,5-pentanediol; and glycerine.

The complex can be produced by reacting at least one metal perchlorate as mentioned above with at least one compound selected from polyhydric alcohols and their derivatives at a weight ratio of preferably

10:90 to 70:30, more preferably 20:80 to 55:45. The complex obtained from the reaction at this weight ratio is a liquid which is transparent to translucent at ordinary temperature and is colorless to yellowish brown. The complex which is the stabilizer component (d) of this invention is used in an amount of preferably 0.2-5 parts by weight, more preferably 0.5-2 parts by weight, per 100 parts by weight of the chlorine-containing resin.

As described above, the chlorine-containing resin composition of this invention comprises the stabilizer components (a) to (d) as essential components. The synergistic effect of these four stabilizer components can prevent the chlorine-containing resin in the composition from being discolored and deteriorated in physical properties accompanying thermal degradation when the composition is subjected to thermoforming and even when the composition is exposed to a high temperature atmosphere for a long period of time. The four stabilizer components also show an excellent effect on the processability (e.g. plate-out) of the chlorine-containing resin composition of this invention.

The chlorine-containing resin composition of this invention may further comprise a known stabilizer for chlorine-containing resins, a known co-stabilizer and other known additives, for example, a metal salt of an organic acid, a metal phenolate, an organic metal salt, an organic ester of phosphorous acid, an antioxidant, a β -diketone compound, an inorganic metal salt compound, an epoxy compound, a light stabilizer, a processing aid, etc.

The metal salt of an organic acid is generally called "metal soap". In this case, the metal is, for example, sodium, potassium, magnesium, calcium, barium or zinc; and the organic acid forming the salt with the metal is a carboxylic acid such as hexanoic acid, octanoic acid, 2-ethylhexanoic acid, decanoic acid, isodecanoic acid, lauric acid, myristic acid, palmitic acid, stearic acid, behenic acid, palmitoleic acid, oleic acid, ricinoleic acid, linoleic acid, isostearic acid, 12-hydroxystearic acid, adipic acid, azelaic acid, sebacic acid, benzoic acid, toluic acid, xylic acid, p-t-butylbenzoic acid, p-t-octylbenzoic acid or a mixture thereof. These metal carboxylates are generally called "non- or low-toxic metal soap".

The phenol of the metal phenolate is, for example, p-t-butylphenol, p-t-octylphenol, nonylphenol, dinonylphenol, decylphenol or dodecylphenol; and the metal is, for example, magnesium, calcium or barium.

The organic metal salt is typically an organotin compound and includes, for example, dimethyltin bis(isooctyl thioglycollate), dibutyltin dilaurate, dibutyltin maleate, dibutyltin bis(mono-C₂₋₁₈ alkyl maleate), dibutyltin bis(isooctyl thioglycollate), dibutyltin thiopropionate, monooctyltin tris(C₁₂₋₁₄ alkyl thioglycollate) and dioctyltin bis(isooctyl thioglycollate).

The organic ester of phosphorous acid, which may optionally be co-used in this invention, is typically a trialkyl phosphite, an alkylaryl phosphite, a bisphenol A type phosphite or a polyol ester type phosphite, and includes specifically triisooctyl phosphite, triisodecyl phosphite, trisnonylphenyl phosphite, diphenylisodecyl phosphite, diphenyltridecyl phosphite, distearyl-pentaerythritol diphosphite, tri-2,4-di-t-butylphenyl phosphite, tetra-C₁₂₋₁₅ alkyl-4,4'-isopropylidenediphenyl diphosphite, tetrakisphenyl-dipropylene glycol diphosphite, tetrakisnonylphenyl-dipropylene glycol diphosphite, poly(dipropylene glycol)phenyl phosphite, etc.

The antioxidant which may optionally be used in this invention is a hindered phenol, for example, 2,6-di-t-butyl-4-methylphenol, 2,2'-methylenebis(4-methyl-6-t-butylphenol) or 4,4'-thiobis(6-t-butyl-3-methylphenol); or an alkyl ester of a sulfur-containing alkanolic acid, for example, dilauryl thiodipropionate, distearyl thiodipropionate or the like.

The β -diketone compound which may optionally be used in this invention includes, for example, benzoylacetone, dibenzoylmethane, myristoylbenzoylmethane, palmitoylbenzoylmethane, stearoylbenzoylmethane, etc.

The co-stabilizer which may optionally be used in this invention is typically an epoxy compound such as epoxidized soybean oil, epoxidized linseed oil, epoxidized castor oil, butyl ester of epoxidized linseed oil fatty acid, butyl or 2-ethylhexyl epoxystearate, diglycidyl ether of bisphenol A or the like. The inorganic compound includes, for example, magnesium oxide, calcium oxide, calcium phosphate, aluminum hydroxide, synthetic hydrotalcite and the like. The light stabilizer is of a benzotriazole compound or a hindered amine compound and specifically includes 2-(3,5-di-t-butyl-2-hydroxyphenyl)benzotriazole, 2-(3,5-di-t-butyl-2-hydroxyphenyl)-5-chlorobenzotriazole, polycondensate of dimethyl succinate with 1-(2-hydroxyethyl)-4-hydroxy-2,2,6,6-tetramethylpiperidine, etc. As the processing aid, an organic phosphorus compound such as nonylphenoxy polyethoxy phosphoric acid, tridecylhydroxy polyethoxy phosphoric acid or the like may be used.

The known stabilizer and the known co-stabilizer mentioned above can be appropriately used in this invention for the purpose of further improving the thermal stability, weather resistance and processability of the chlorine-containing resin composition of this invention.

The chlorine-containing resin in this invention includes, for example, a vinyl chloride homopolymer; a vinyl chloride-vinyl acetate copolymer; copolymers of a vinyl chloride and an ethylenically unsaturated

monomer, for example, a vinyl chloride-propylene copolymer and the like; copolymers of a vinyl chloride and a conjugated diene, for example, a vinyl chloride-butadiene copolymer and the like; a vinyl chloride-urethane copolymer; a vinyl chloride-ethylene-vinyl acetate terpolymer; and a blend of one of these (co)-polymers with a chlorinated polyethylene, a chlorinated polypropylene, a polyurethane, an acrylonitrile-butadiene-styrene terpolymer, a methacrylic acid ester-butadiene-styrene terpolymer or an acrylonitrile-butadiene copolymer.

The vinyl chloride copolymers mentioned above has a bound vinyl chloride content of at least 60% by weight.

The chlorine-containing resin is preferably a mixture of 100 parts by weight of a polyvinyl chloride and 20-120 parts by weight of a plasticizer.

The chlorine-containing resin composition of this invention can be molded into semi-rigid to flexible articles depending upon the applications of the molded articles, by varying the amount of the plasticizer (e.g. trimellitic acid ester or the like) used. If necessary, the chlorine-containing resin composition can comprise appropriate amounts of a filler, a pigment, an anti-static agent, an anti-fogging agent, a flame retardant, an antifungal agent, a crosslinking agent, a blowing agent and other auxiliary reagents.

This invention is specifically described below referring to Examples.

Synthesis Example 1

120 g (1 mole) of diethylene glycol monomethyl ether was heated with stirring. When the temperature thereof reached 80°C, 112 g (0.8 mole) of sodium perchlorate monohydrate was added in small portions to suspend it in diethylene glycol monoethyl ether. The temperature of the resulting suspension was gradually elevated to 100°C while stirring the suspension, upon which the suspension became a solution. The solution thus formed was further heated gradually, whereby the reaction proceeded with mild heat generation. Then, the reaction mixture was distilled at 110°C under reduced pressure, to remove the calculated amount of water, thereby completing the reaction. As a result, 215 g of a yellow, transparent, liquid complex was obtained.

Synthesis Example 2

The same procedure as in Synthesis Example 1 was repeated, except that 115 g (0.6 mole) of tripropylene glycol was substituted for the 120 g of diethylene glycol monomethyl ether, to obtain 210 g of a light yellow, transparent, liquid complex.

Synthesis Example 3

The same procedure as in Synthesis Example 1 was repeated, except that 138 g (1 mole) of ethylene glycol monophenyl ether was substituted for the 120 g of diethylene glycol monomethyl ether and 138 g (0.5 mole) of magnesium perchlorate trihydrate was substituted for the 112 g of sodium perchlorate monohydrate, to obtain 245 g of a yellow, transparent, liquid complex.

Synthesis Example 4

The same procedure as in Synthesis Example 3 was repeated, except that 129 g (1.1 mole) of ethylene glycol monobutyl ether was substituted for the 138 g of ethylene glycol monophenyl ether to obtain 235 g of a yellow, transparent, liquid complex.

Synthesis Example 5

The same procedure as in Synthesis Example 1 was repeated, except that 134 g (1 mole) of dipropylene glycol was substituted for the 120 g of diethylene glycol monomethyl ether and 155 g (0.5 mole) of calcium perchlorate tetrahydrate was substituted for the 112 g of sodium perchlorate monohydrate.

Synthesis Example 6

The same procedure as in Synthesis Example 1 was repeated, except that 118 g (1 mole) of ethylene glycol monobutyl ether was substituted for the 120 g of diethylene glycol monomethyl ether and 117 g (0.3 mole) of barium perchlorate trihydrate was substituted for the 112 g of sodium perchlorate monohydrate.

Each of the complexes [the stabilizer component (d) of this invention] obtained in Synthesis Examples 1-6 was measured for infrared absorption spectrum using an infrared spectrophotometer. As a result, the complexes showed characteristic absorptions of $\text{Me}(\text{ClO}_4)_n$ at $1140\text{--}1060\text{ cm}^{-1}$ and 630 cm^{-1} , and those of $\text{R}(\text{OH})_p$ at $3600\text{--}3200\text{ cm}^{-1}$.

Also, the liquid complexes obtained in Synthesis Examples 1-6 were subjected to test for evaluation of dangerousness of unstable substances, by the following test method which is described in T. Yoshida, "Kagakuyakuhin no Anzen" (Safety of Chemicals), 1982:

(a) Test for heat-generatability and stability by differential scanning calorimetry

None of the liquid complexes obtained in Synthesis Examples 1-6 exhibited such behavior as heat generation or the like in a temperature range of $60\text{--}220^\circ\text{C}$ and all of them were stable in the temperature range.

(b) Dewar vessel test

A storage test at constant temperature under heat accumulation conditions was conducted by storing a sample at a temperature of 150°C for 168 hours to evaluate its degradability under heat accumulation conditions. As a result, none of the liquid complexes obtained in Synthesis Examples 1-6 showed such behaviors as heat generation, thermal degradation and the like due to heat-accumulation.

These test results indicated that none of the complexes obtained above had fear of heat generation, thermal degradation, etc.

Examples 1-8 and Comparative Examples 1-5

In order to examine the thermal stability, processability, etc. of the chlorine-containing resin composition of this invention containing the stabilizer components (a) to (d), various tests were conducted using the following compounds:

Formulation	
Vinyl chloride resin ^{*1}	100 parts by weight
Plasticizer ^{*2}	60 parts by weight
Epoxidized soybean oil	3 parts by weight
Organic ester of phosphorons acid ^{*3} Stabilizer (See Table 1)	0.8 part by weight (See Table 1)
Fine powder vinyl chloride resin for paste ^{*4}	15 parts by weight

Note:

^{*1} Zeon 103 EP-8, a product of Nippon Zeon Co., Ltd., having an average polymerization degree of 800

^{*2} Vynecizer N-80 (tri-n-octyl trimellitate), a product of Kao Corp.

^{*3} Tetraalkyl($\text{C}_{12}\text{--}15$)bisphenol A diphosphite

^{*4} A fine powder for paste, having an average polymerization degree of 850 and containing 90% or more of particles which pass through a 200-mesh (Tyler) screen.

(1) Preparation of resin composition in the powder form

Into a 20-liter Henschel mixer was charged 2,000 g of a vinyl chloride resin, and the number of revolutions of the mixer was set at 1,000 rpm. Then, the stabilizer was added to the resin in an amount as indicated in the above formulation, and the resulting mixture was stirred with heating. When the temperature reached 60°C , the epoxidized soybean oil and the plasticizer were added to the mixture in this order, and stirring was further effected with heating. The temperature of the resin composition reached 120°C , and the stirring (dry blending) was continued for 30 minutes at that temperature. The mixture in the Henschel mixer was cooled with water. At 40°C , 300 g of the fine powder vinyl chloride resin for paste was added to the cooled mixture, and stirring was effected for 5 minutes to obtain a vinyl chloride resin composition in the powder form.

(2) Preparation of sheet

A nickel-chromium steel plate having a size of 300 mm x 300 mm x 1.5 mm (thickness) was heated in a Geer given at 240°C and then taken out. On the mirror surface of the plate, 200 g of the resin composition in the powder form prepared in (1) above was sprinkled in the form of a disc of 200 mm in diameter. The resin composition on the surface was allowed to stand for 10 seconds to fusion-bond particles of the resin to the plate. Then, the unbonded particles of the resin composition was wiped off. The plate with the fused resin was placed again in the Geer oven at 240°C for 50 seconds to melt the resin, after which the plate with the molten resin was taken out of the oven and immediately subjected to rapid cooling. A resin sheet of 200 mm in diameter and 0.75 mm in thickness was separated from the plate.

This sheet was subjected to the following tests.

Test 1

- (a) The sheet was placed in a Geer oven at 260°C for a given period of time and then examined for the discoloration due to thermal degradation and the time taken until the sheet resin was decomposed to black.
- (b) The sheet was also examined for peelability from the plate and staining on the mirror surface of the plate (plate-out) when the sheet was separated from the plate.
- The results of Test 1 are shown in Table 2.

(3) Integral molding with urethane foam

The sheet obtained by the method of (2) above was set in a metal mold. On this sheet set in the metal mold was poured a starting mixture for urethane foam, obtained by stirring a polyol (EP-3033, a product of Mitsui Toatsu Chemicals, Inc.) and a polyisocyanate (MDI-CR-200, a product of the same company) in a weight ratio of 10:7. The starting mixture for urethane foam was then foamed, to obtain an integrally molded article of 20 mm in thickness, consisting of a vinyl chloride sheet and an urethane foam.

The molded article was subjected to the following test.

Test 2

- (a) The molded article was placed in a Geer oven heated at 120°C for a long period of time to examine the discoloration due to heat accumulation. When 200 hours elapsed in the course of the heating, blooming or bleeding was examined.
- (b) The molded article heated at 120°C for a long period of time was tested for elongation (%) in accordance with JIS K 7113-81 "Method of Tensile Test of Plastics".

The results of Test 2 are shown in Table 3.

Table 1

	Components of stabilizer (parts by weight)					
	Overbased alkaline earth metal salt (a)		Zeo- lite (b)	Calcium hydroxide (c)	Complex (d)	
	Kind	Amount			Kind	Amount
Ex. 1	Overbased barium nonylphenolate carbonate (Ba 28%)	0.7	1.5	3.0	Syn. Ex. 1	1.2
Ex. 2	"	0.7	1.5	3.0	Syn. Ex. 3	1.5
Ex. 3	"	0.7	1.5	3.0	Syn. Ex. 5	1.5
Ex. 4	"	0.7	1.5	3.0	Syn. Ex. 6	1.5
Ex. 5	Overbased barium oleate (Ba 34%)	0.5	1.5	3.0	Syn. Ex. 2	1.2
Ex. 6	Lubrizol LD 2105 (Ca 7.2%)	2.5	1.5	3.0	Syn. Ex. 1	1.2
Ex. 7	Lubrizol LD 2106 (Ba 27.5%)	0.7	1.5	3.0	Syn. Ex. 4	1.2
Ex. 8	Lubrizol LZ 2116 (Ba 34%)	0.5	1.5	3.0	Syn. Ex. 2	1.2

- Cont'd -

Table 1 (Cont'd)

Comp. Ex. 1	Overbased barium oleate (Ba 34%)	0.5	-	-	-	Syn. Ex. 1	0.2
Comp. Ex. 2	-	-	1.5	3.0	-	Syn. Ex. 1	1.2
Comp. Ex. 3	Overbased barium nonylphenolate carbonate (Ba 28%)	0.7	1.5	3.0	-	-	-
Comp. Ex. 4	Barium oleate	0.9	1.5	3.0	-	Syn. Ex. 1	1.2
Comp. Ex. 5	Overbased barium nonylphenolate carbonate (Ba 28%)	0.7	1.5	3.0	-	NaClO ₄	0.54
Comp. Ex. 6 (Control)	-	-	-	-	-	-	-

Table 2
(Test 1)

Kind of stabilizer	Color of sheet heated at 260°C in Geer oven					Peelability from metal mold	Metal mold staining
	Original sheet	After 2 min.	After 4 min.	After 8 min.	After 15 min.		
Example 1	Colorless	Colorless	Slightly yellow	Yellow	Brown	Good	Good
Example 2	Colorless	Colorless	Slightly yellow	Yellowish brown	Brown	Good	Good
Example 3	Colorless	Colorless	Slightly yellow	Yellowish brown	Brown	Good	Good
Example 4	Colorless	Colorless	Slightly yellow	Yellowish brown	Brown	Good	Good
Example 5	Colorless	Colorless	Colorless	Yellow	Brown	Very good	Very good
Example 6	Colorless	Colorless	Colorless	Yellow	Black in 12 minutes	Good	Good
Example 7	Colorless	Colorless	Slightly yellow	Brown	Brown	Good	Good
Example 8	Colorless	Colorless	Colorless	Yellow	Brown	Very good	Very good

- Cont'd -

Table 2 (Cont'd)

Comparative Example 1	Colorless	Slightly yellow	Black	-	Black in 3.5 min.	Bad	Bad
Comparative Example 2	Colorless	Slightly yellow	Yellowish brown	Brown	Black	Medial	Bad
Comparative Example 3	Slightly yellow	Slightly yellow	Yellow	Brown	Brown	Medial	Medial
Comparative Example 4	Colorless	Slightly yellow	Yellow	Yellowish brown	Black	Good	Bad
Comparative Example 5	Slightly yellow	Slightly yellow	Yellow	Brown	Partially black	Medial	Medial
Comparative Example 6 (Control)	Yellow	Yellowish brown	Black	-	Black in 2.5 min.	Very bad	Medial

Table 3
(Test 2)

Kind of stabilizer	Color of sheet heated at 120°C						Elongation (%)	
	After 96 hr.	After 200 hr.		After 300 hr.	After 400 hr.	Original sheet	After 300 hr.	
		Color	Blooming or bleeding					
Example 1	colorless	Slightly yellow	Good	Yellow	Yellowish brown	305	210	
Example 2	Slightly yellow	Slightly yellow	Good	Yellowish brown	Brown	290	200	
Example 3	Slightly yellow	Slightly yellow	Good	Yellowish brown	Brown	295	205	
Example 4	Slightly yellow	Slightly yellow	Good	Yellowish brown	Brown	308	210	
Example 5	colorless	Slightly yellow	Good	Yellow	Yellowish brown	310	215	
Example 6	colorless	colorless	Slightly good	Yellow	Brown	288	197	
Example 7	colorless	colorless	Good	Yellowish brown	Brown	302	203	
Example 8	colorless	Slightly yellow	Good	Yellow	Yellow	305	208	

- Cont'd -

Table 3 (Cont'd)

Comparative Example 1	Slightly yellow	Yellow	Very bad	Brown	Black	321	210
Comparative Example 2	Slightly yellow	Yellow	Bad	Brown	Black	250	150
Comparative Example 3	Slightly yellow	Brown	Medial	Dark brown	-	260	33
Comparative Example 4	Slightly yellow	Yellow	Bad	Yellowish brown	Black	280	165
Comparative Example 5	Slightly yellow	Brown	Bad	Dark brown	-	269	66
Comparative Example 6 (control)	Yellow	Yellowish brown	Medial	Black	-	160	-

Claims

1. A thermally stabilized chlorine-containing resin composition comprising a chlorine-containing resin and a stabilizer consisting essentially of (a) an overbased alkaline earth metal carboxylate or phenolate complex, (b) zeolite, (c) calcium hydroxide and (d) a complex of at least one metal perchlorate selected

from the group consisting of sodium, magnesium, calcium and barium perchlorates with at least one compound selected from the group consisting of polyhydric alcohols and their derivatives.

2. A composition according to Claim 1, wherein the chlorine-containing resin is a vinyl chloride homopolymer, a copolymer of vinyl chloride and an ethylenically unsaturated monomer, a vinyl chloride-vinyl acetate copolymer or a vinyl chloride-ethylene-vinyl acetate terpolymer, the copolymers and the terpolymer having a bound vinyl chloride content of at least 60% by weight.
3. A composition according to Claim 1, which further contains, as a blending polymer, at least one polymer selected from the group consisting of a methacrylate-butadiene-styrene terpolymer, an acrylonitrile-butadiene copolymer and a polyurethane.
4. A composition according to Claim 1, wherein the chlorine-containing resin is a mixture of 100 parts by weight of a polyvinyl chloride and 20-120 parts by weight of a plasticizer.
5. A composition according to Claim 1, wherein the component (a) of the stabilizer is overbased barium isodecanoate, overbased barium oleate, overbased barium linoleate, overbased calcium isodecanoate, overbased calcium oleate, overbased magnesium oleate, overbased barium dodecylphenolate carbonate, overbased barium octylphenolate carbonate, overbased calcium dodecylphenolate carbonate, overbased calcium thiobisdodecylphenolate carbonate or overbased magnesium nonylphenolate carbonate.
6. A composition according to Claim 1, wherein the component (a) of the stabilizer is overbased barium octylphenolate carbonate, overbased barium dodecylphenolate carbonate, overbased calcium dodecylphenolate carbonate or overbased magnesium nonylphenolate carbonate.
7. A composition according to Claim 1, wherein the component (a) of the stabilizer is overbased barium 2-ethylhexanoate, overbased barium oleate, overbased barium linoleate, overbased calcium isodecanoate, overbased calcium oleate or overbased magnesium oleate.
8. A composition according to Claim 1, wherein the component (a) of the stabilizer is contained in an amount of 0.1-4 parts by weight per 100 parts by weight of the chlorine-containing resin.
9. A composition according to Claim 1, wherein the component (a) of the stabilizer is contained in an amount of 0.2-2 parts by weight per 100 parts by weight of the chlorine-containing resin.
10. A composition according to Claim 1, wherein the component (b) of the stabilizer is a synthetic A type zeolite represented by $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot y\text{H}_2\text{O}$ ($0.5 \leq x \leq 3$ and $0.5 \leq y \leq 6$).
11. A composition according to Claim 1, wherein the component (b) of the stabilizer is a synthetic A type zeolite represented by $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot 4.5\text{H}_2\text{O}$.
12. A composition according to Claim 1, wherein the component (b) of the stabilizer is zeolite particles having a weight average particle diameter of 10 microns or less and contained in an amount of 0.1-5 parts by weight per 100 parts by weight of the chlorine-containing resin.
13. A composition according to Claim 12, wherein the component (b) of the stabilizer is contained in an amount of 0.5-2 parts by weight per 100 parts by weight of the chlorine-containing resin.
14. A composition according to Claim 1, wherein the component (c) of the stabilizer is contained in an amount of 0.5-8 parts by weight per 100 parts by weight of the chlorine-containing resin.
15. A composition according to Claim 1, wherein the component (c) of the stabilizer is in the form of particles having a weight average particle diameter of 10 microns or less and contained in an amount of 1-5 parts by weight per 100 parts by weight of the chlorine-containing resin.
16. A composition according to Claim 1, wherein the component (d) of the stabilizer is a complex represented by $[\text{Me}(\text{ClO}_4)_n][\text{R}(\text{OH})_p]_q$ (Me is sodium, magnesium, calcium or barium, n is an integer of

1 or 2, p is an integer of 1-3, q is an arbitrary number of 1-6, R is the residue of polyhydric alcohol or its derivative, and qR's may be the same or different), the complex being liquid at ordinary temperature.

- 5 17. A composition according to Claim 16, wherein R is the residue of at least one compound selected from the group consisting of ethylene glycol, ethylene glycol mono-C₁₋₄alkyl ethers and ethylene glycol monophenyl ether.
18. A composition according to Claim 16, wherein R is the residue of at least one compound selected from
10 the group consisting of diethylene glycol and diethylene glycol mono-C₁₋₄alkyl ethers.
19. A composition according to Claim 16, wherein R is the residue of at least one compound selected from the group consisting of propylene glycol and propylene glycol mono-C₁₋₄alkyl ethers.
- 15 20. A compositions according to Claim 16, wherein R is the residue of at least one compound selected from the group consisting of triethylene glycol, polyethylene glycol, dipropylene glycol and tripropylene glycol.
21. A composition according to Claim 1, wherein the component (d) of the stabilizer is a complex obtained
20 by reacting at least one metal perchlorate selected from the group consisting of sodium, magnesium, calcium and barium perchlorates, with at least one compound selected from the group consisting of polyhydric alcohols and their derivatives in a weight ratio of from 10 : 90 to 70 : 30.
22. A composition according to Claim 21, wherein the weight ratio is from 20 : 80 to 55 : 45.
25
23. A composition according to Claim 1, wherein the stabilizer component (d) is contained in an amount of 0.2-5 parts by weight per 100 parts by weight of the chlorine-containing resin.
24. A composition according to Claim 1, wherein the stabilizer component (d) is contained in an amount of
30 0.5-2 parts by weight per 100 parts by weight of the chlorine-containing resin.
25. A composition according to Claim 1, which further comprises at least one metal soap selected from the group consisting of magnesium, calcium, barium and zinc salts of organic acids.
- 35 26. A composition according to Claim 1, which further comprises at least one organic ester of phosphorous acid selected from the group consisting of trialkyl type phosphites, alkylaryl type phosphites, bisphenol A type phosphites and polyol ester type phosphites.
27. A composition according to Claim 1, which further comprises a β -diketone compound or an epoxy
40 compound.

Patentansprüche

- 45 1. Thermisch stabilisierte chlorhaltige Harzzusammensetzung mit Gehalt an chlorhaltigem Harz und einem Stabilisator, im wesentlichen bestehend aus (a) einem überbasischen Erdalkalimetallcarboxylat oder -phenolatkomplex, (b) Zeolith, (c) Calciumhydroxid und (d) einem Komplex von mindestens einem der Metallperchlorate von Natrium, Magnesium, Calcium und/oder Barium mit mindestens einer der Verbindungen polyhydrische Alkohole und/oder ihre Derivate.
- 50 2. Zusammensetzung nach Anspruch 1, wobei das chlorhaltige Harz ein Vinylchloridhomopolymer, ein Copolymer von Vinylchlorid und einem ethylenisch ungesättigten Monomeren, ein Vinylchlorid-Vinylacetatcopolymer oder ein Vinylchlorid-Ethylenvinylacetatpolymer, wobei die Copolymeren und das Terpolymer einen gebundenen Vinylchloridgehalt von mindestens 60 Gew.% aufweisen.
- 55 3. Zusammensetzung nach Anspruch 1, die darüber hinaus als Mischungspolymer zumindest ein Methacrylat-Butadien-Styrolterpolymer, ein Acrylnitril-Butadiencopolymer und/oder ein Polyurethan enthält.

4. Zusammensetzung nach Anspruch 1, wobei das chlorhaltige Harz eine Mischung von 100 Gewichtsteilen eines Polyvinylchlorids und 20 bis 120 Gewichtsteilen eines Weichmachers ist.
5. Zusammensetzung nach Anspruch 1, wobei die Komponente (a) des Stabilisators überbasisches Bariumisodecanoat, überbasisches Bariumoleat, überbasisches Bariumlinoleat, überbasisches Bariumlinoleat, überbasisches Calciumisodecanoat, überbasisches Calciumoleat, überbasisches Magnesiumoleat, überbasisches Bariumdodecylphenolatcarbonat, überbasisches Bariumoctylphenolatcarbonat, überbasisches Calciumdodecylphenolatcarbonat, überbasisches Calciumthiobisdodecylphenolatcarbonat und/oder überbasisches Magnesiumnonylphenolatcarbonat ist.
6. Zusammensetzung nach Anspruch 1, wobei die Komponente (a) des Stabilisators überbasisches Bariumoctylphenolatcarbonat, überbasisches Bariumdodecylphenolatcarbonat, überbasisches Calciumdodecylphenolatcarbonat und/oder überbasisches Magnesiumnonylphenolatcarbonat ist.
7. Zusammensetzung nach Anspruch 1, wobei die Komponente (a) des Stabilisators überbasisches Barium-2-ethylhexanoat, überbasisches Bariumoleat, überbasisches Bariumlinoleat, überbasisches Calciumisodecanoat, überbasisches Calciumoleat und/oder überbasisches Magnesiumoleat ist.
8. Zusammensetzung nach Anspruch 1, wobei die Komponente (a) des Stabilisators in Mengen von 0,1 bis 4 Gewichtsteilen je 100 Gewichtsteile chlorhaltiges Harz enthalten ist.
9. Zusammensetzung nach Anspruch 1, wobei die Komponente (a) des Stabilisators in Mengen von 0,2 bis 2 Gew.% je 100 Gewichtsteile chlorhaltiges Harz enthalten ist.
10. Zusammensetzung nach Anspruch 1, wobei die Komponente (b) des Stabilisators ein synthetischer Zeolith vom Typ A gemäß $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot y\text{H}_2\text{O}$ ($0,5 \leq x \leq 3$ und $0,5 \leq y \leq 6$) ist.
11. Zusammensetzung nach Anspruch 1, wobei die Komponente (b) des Stabilisators ein synthetischer Zeolith vom Typ A gemäß $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot 4,5\text{H}_2\text{O}$ ist.
12. Zusammensetzung nach Anspruch 1, wobei die Komponente (b) des Stabilisators Zeolithpartikel sind, die einen (Gewichts-) mittleren Partikeldurchmesser von 10 Mikron oder weniger aufweisen und in Mengen von 0,1 bis 5 Gewichtsteilen je 100 Gewichtsteile des chlorhaltigen Harzes enthalten sind.
13. Zusammensetzung nach Anspruch 12, wobei die Komponente (b) des Stabilisators in Mengen von 0,5 bis 2 Gewichtsteilen je 100 Gewichtsteile des chlorhaltigen Harzes enthalten ist.
14. Zusammensetzung nach Anspruch 1, wobei die Komponente (c) des Stabilisators in Mengen von 0,5 bis 8 Gewichtsteilen je 100 Gewichtsteile des chlorhaltigen Harzes enthalten ist.
15. Zusammensetzung nach Anspruch 1, wobei die Komponente (c) des Stabilisators in Form von Partikeln mit einem (Gewichts-) mittlerem Partikeldurchmesser von 10 Mikron oder weniger und in Mengen von 1 bis 5 Gewichtsteilen je 100 Gewichtsteile des chlorhaltigen Harzes enthalten ist.
16. Zusammensetzung nach Anspruch 1, wobei die Komponente (d) des Stabilisators ein Komplex gemäß $[\text{Me}(\text{ClO}_4)_n][\text{R}(\text{OH})_p]_q$ (Me ist Natrium, Magnesium, Calcium und/oder Barium, n ist eine ganze Zahl von 1 oder 2, p ist eine ganze Zahl von 1 bis 3, q ist eine Zahl von 1 bis 6, R ist der Rest eines polyhydricen Alkohols oder dessen Derivats, und qR' können gleich oder verschieden sein) ist, wobei der Komplex bei normaler Temperatur flüssig ist.
17. Zusammensetzung nach Anspruch 16, wobei R der Rest von mindestens einer der Verbindungen Ethylenglykol, Ethylenglykolmono- C_{1-4} alkylether und/oder Ethylenglykolmonophenylether ist.
18. Zusammensetzung nach Anspruch 16, wobei R der Rest von mindestens einer der Verbindungen Diethylenglykol und/oder Diethylenglykolmono- C_{1-4} alkylether ist.
19. Zusammensetzung nach Anspruch 16, wobei R der Rest von mindestens einer der Verbindungen Propylenglykol und/oder Propylenglykolmono- C_{1-4} alkylether ist.

20. Zusammensetzung nach Anspruch 16, wobei R der Rest mindestens einer der Verbindungen Triethylenglykol, Polyethylenglykol, Dipropylenglykol und/oder Tripropylenglykol ist.
21. Zusammensetzung nach Anspruch 1, wobei die Komponente (d) des Stabilisators ein Komplex ist, der erhalten wird durch Umsetzung von mindestens einem der Metallperchlorate von Natrium, Magnesium, Calcium und/oder Barium mit mindestens einer der Verbindungen polyhydriche Alkohole und/oder ihre Derivate im Gewichtsverhältnis von 10 : 90 bis 70 : 30.
22. Zusammensetzung nach Anspruch 21, wobei das Gewichtsverhältnis von 20 : 80 bis 55 : 45 beträgt.
23. Zusammensetzung nach Anspruch 1, wobei die Stabilisatorkomponente (d) in Mengen von 0,2 bis 5 Gewichtsteilen je 100 Gewichtsteile chlorhaltiges Harz enthalten ist.
24. Zusammensetzung nach Anspruch 1, wobei die Stabilisatorkomponente (d) in Mengen von 0,5 bis 2 Gewichtsteilen je 100 Gewichtsteile chlorhaltiges Harz enthalten ist.
25. Zusammensetzung nach Anspruch 1, die zusätzlich mindestens eine der Metallseifen von Magnesium, Calcium, Barium und/oder Zinksalze organischer Säuren enthält.
26. Zusammensetzung nach Anspruch 1, die zusätzlich mindestens einen der organischen Ester der Phosphorsäure Trialkylphosphite, Alkylarylphosphite, Bisphenol A Phosphite und/oder Polyolesterphosphite enthält.
27. Zusammensetzung nach Anspruch 1, die zusätzlich eine β -Diketonverbindung und/oder eine Epoxyverbindung enthält.

Revendications

1. Composition de résine chlorée stabilisée à la chaleur, comprenant une résine chlorée et un stabilisant qui se compose essentiellement: (a) d'un complexe de carboxylate ou de phénolate de métal alcalino-terreux surbasifié, (b) d'une zéolithe, (c) d'hydroxyde de calcium et (d) d'un complexe d'au moins un perchlorate métallique choisi dans le groupe constitué par les perchlorates de sodium, de magnésium, de calcium et de baryum, avec au moins un composé choisi dans le groupe constitué par les polyalcools et leurs dérivés.
2. Composition selon la revendication 1, dans laquelle la résine chlorée est un homopolymère de chlorure de vinyle, un copolymère de chlorure de vinyle et d'un monomère à insaturation éthylénique, un copolymère chlorure de vinyle/acétate de vinyle ou un terpolymère chlorure de vinyle/éthylène/acétate de vinyle, les copolymères et le terpolymère ayant une teneur en chlorure de vinyle lié d'au moins 60% en poids.
3. Composition selon la revendication 1, contenant en outre, en tant que polymère de mélange, au moins un polymère choisi dans le groupe constitué par un terpolymère méthacrylate/butadiène/styrène, un copolymère acrylonitrile/butadiène et un polyuréthane.
4. Composition selon la revendication 1, dans laquelle la résine chlorée est un mélange de 100 parties en poids d'un polychlorure de vinyle et de 20 à 120 parties en poids d'un plastifiant.
5. Composition selon la revendication 1, dans laquelle le composant (a) du stabilisant est l'isodécanoate de baryum surbasifié, l'oléate de baryum surbasifié, le linoléate de baryum surbasifié, l'isodécanoate de calcium surbasifié, l'oléate de calcium surbasifié, l'oléate de magnésium surbasifié, le dodécylphénolate-carbonate de baryum surbasifié, l'octylphénolate-carbonate de baryum surbasifié, le dodécyl-nonylphénolate-carbonate de calcium surbasifié, le thiobisdodécylphénolate-carbonate de calcium surbasifié ou le nonylphénolate-carbonate de magnésium surbasifié.
6. Composition selon la revendication 1, dans laquelle le composant (a) du stabilisant est l'octylphénolate-carbonate de baryum surbasifié, le dodécylphénolate-carbonate de baryum surbasifié, le dodécyl-nonylphénolate-carbonate de calcium surbasifié ou le nonylphénolate-carbonate de magnésium surbasifié.

7. Composition selon la revendication 1, dans laquelle le composant (a) du stabilisant est le 2-éthylhexanoate de baryum surbasifié, l'oléate de baryum surbasifié, le linoléate de baryum surbasifié, l'isodécanoate de calcium surbasifié, l'oléate de calcium surbasifié ou l'oléate de magnésium surbasifié.
- 5 8. Composition selon la revendication 1, dans laquelle le composant (a) du stabilisant est contenu dans une proportion de 0,1 à 4 parties en poids pour 100 parties en poids de la résine chlorée.
9. Composition selon la revendication 1, dans laquelle le composant (a) du stabilisant est contenu dans une proportion de 0,2 à 2 parties en poids pour 100 parties en poids de la résine chlorée.
- 10 10. Composition selon la revendication 1, dans laquelle le composant (b) du stabilisant est une zéolithe synthétique de type A, représentée par $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot y\text{H}_2\text{O}$ ($0,5 \leq x \leq 3$ et $0,5 \leq y \leq 6$).
- 15 11. Composition selon la revendication 1, dans laquelle le composant (b) du stabilisant est une zéolithe synthétique de type A, représentée par $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot x\text{SiO}_2 \cdot 4,5\text{H}_2\text{O}$.
12. Composition selon la revendication 1, dans laquelle le composant (b) du stabilisant est constitué par des particules de zéolithe ayant un diamètre en moyenne pondérale de 10 μm ou moins et contenues dans une proportion de 0,1 à 5 parties en poids pour 100 parties en poids de la résine chlorée.
- 20 13. Composition selon la revendication 12, dans laquelle le composant (b) du stabilisant est contenu dans une proportion de 0,5 à 2 parties en poids pour 100 parties en poids de la résine chlorée.
14. Composition selon la revendication 1, dans laquelle le composant (c) du stabilisant est contenu dans une proportion de 0,5 à 8 parties en poids pour 100 parties en poids de la résine chlorée.
- 25 15. Composition selon la revendication 1, dans laquelle le composant (c) du stabilisant est sous la forme de particules ayant un diamètre en moyenne pondérale de 10 μm ou moins et contenues dans une proportion de 1 à 5 parties en poids pour 100 parties en poids de la résine chlorée.
- 30 16. Composition selon la revendication 1, dans laquelle le composant (d) du stabilisant est un complexe représenté par $[\text{Me}(\text{ClO}_4)_n][\text{R}(\text{OH})_p]_q$ (Me étant un atome de sodium, de magnésium, de calcium ou de baryum, n étant le nombre entier 1 ou 2, p étant un nombre entier de 1 à 3, q étant un nombre arbitraire de 1 à 6, R étant le résidu d'un polysilcol ou d'un dérivé de celui-ci et les qR pouvant être identiques ou différents), le complexe étant liquide à la température ordinaire.
- 35 17. Composition selon la revendication 16, dans laquelle R est le résidu d'au moins un composé choisi dans le groupe constitué par l'éthylèneglycol, les éthers monoalkyliques en $\text{C}_1\text{-C}_4$ d'éthylèneglycol et l'éther monophénylique d'éthylèneglycol.
- 40 18. Composition selon la revendication 16, dans laquelle R est le résidu d'au moins un composé choisi dans le groupe constitué par le diéthylèneglycol et les éthers monoalkyliques en $\text{C}_1\text{-C}_4$ de diéthylèneglycol.
- 45 19. Composition selon la revendication 16, dans laquelle R est le résidu d'au moins un composé choisi dans le groupe constitué par le propylèneglycol et les éthers monoalkyliques en $\text{C}_1\text{-C}_4$ de propylèneglycol.
- 50 20. Composition selon la revendication 16, dans laquelle R est le résidu d'au moins un composé choisi dans le groupe constitué par le triéthylèneglycol, le polyéthylèneglycol, le dipropylèneglycol et le tripropylèneglycol.
- 55 21. Composition selon la revendication 1, dans laquelle le composant (d) du stabilisant est un complexe obtenu en faisant réagir au moins un perchlorate métallique choisi dans le groupe constitué par les perchlorates de sodium, de magnésium, de calcium et de baryum, avec au moins un composé choisi dans le groupe constitué par les polyalcools et leurs dérivés, dans un rapport pondéral de 10 : 90 à 70 : 30.

22. Composition selon la revendication 21, dans laquelle le rapport pondéral est compris entre 20 : 80 et 55 : 45.
- 5 23. Composition selon la revendication 1, dans laquelle le composant (d) du stabilisant est contenu dans une proportion de 0,2 à 5 parties en poids pour 100 parties en poids de la résine chlorée.
24. Composition selon la revendication 1, dans laquelle le composant (d) du stabilisant est contenu dans une proportion de 0,5 à 2 parties en poids pour 100 parties en poids de la résine chlorée.
- 10 25. Composition selon la revendication 1, comprenant en outre au moins un savon métallique choisi dans le groupe constitué par les sels de magnésium, de calcium, de baryum et de zinc des acides organiques.
- 15 26. Composition selon la revendication 1, comprenant en outre au moins un ester organique d'acide phosphoreux choisi dans le groupe constitué par les phosphites de type trialkylique, les phosphites de type alkylarylique, les phosphites du type du bisphénol A et les phosphites du type des esters de polyol.
- 20 27. Composition selon la revendication 1, comprenant en outre un composé β -dicétonique ou un composé époxy.

25

30

35

40

45

50

55

THIS PAGE BLANK (USPTO)